



"Super Smooth Knitted Backlit Fabric"

SPA-260 FR



SPECIFICATIONS	IMPERIAL	TEST METHOD
Material	100% polyester	DIN 60001, ASTM D7641
Weight	270g/sq.m, 7.9oz/sq.yd	ISO536
Yarn	60*40 denier	DIN EN ISO 2060, ASTM D 1907
Weave Method	Warp-knitted 3 bar	
Shrinkage	≤2 %	200 °C, 45s
Elasticity	3~5%	"Length*Width=200*50mm, Speed=100mm/min, Tension=20N"
Flame Resistance	DIN 4102-1-B1, NFPA 701	DIN 4102-1-B1, NFPA 701 Test 1
Recommend Fixation Temperature	190-200 °C, 45s	
Yellowing Temperature	≥210 °C	SUPRKC REX-C400, 30s
Maximum Width	3.2m	
Standard Length	100m	DIN EN ISO 3759, ASTM D751-2006
Compatible Inks	Dye-sub Transfer, Dye-sub Direct	
Application	Self signs, Display Systems, Backlit, SEG	