

Deco Display Fabric

SP-220 FR



SPECIFICATIONS	IMPERIAL	TEST METHOD
Material	100% polyester	DIN 60001,ASTM D7641
Weight	220g/sq.m,6.5 oz/sq.yd	ISO536
Yarn	75×40×40 denier	DIN EN ISO 2060,ASTM D1907
Weave Method	Warp-knitted 3 bar	
Opacity	>80%	ISO2471
Elasticity	3~5%	Length*Width=200*50mm, Speed=100mm/min,Tension=20N
Shrinkage	≤2%	200°C , 45s
Flame Resistance	DIN 4102-1-B1,NFPA 701	DIN 4102-1-B1,NFPA 701 Test1
Recommend Fixation Temperature	190-200 C , 45s	
Yellowing Temperature	≥210°C	SUPRKC REX-C400,30s
Maximum Width	3.2m	
Standard Length	100m	DIN EN ISO 3759,ASTM D751-2006
Compatible Inks	Dye-sub Transfer,Dye-sub Direct,Latex	
Application	Display Pop-up,Backdrops	