

**PD-100FR**

SPECIFICATIONS	IMPERIAL	TEST METHOD
Material	100% polyester	DIN 60001, ASTM D7641
Weight	100g/sq.m, 2.9 oz/sq.yd	ISO536
Yarn	100*2X100*2 denier	DIN EN ISO 2060,ASTM D1907
Weave Method	Woven	
Shrinkage	≤4%	200°C, 45s
Opacity	>70%	ISO2471
Elasticity	Warp:(2±1)% Weft:(2±1)%	Length*Width=200*50mmSpeed =100mm/min, Tension=20N
Recommend Fixation Temperature	190-200°C,45s	
Yellowing Temperature	≥210°C	SUPRKC REX-C400,30s
Maximum Width	3.2m	DIN EN ISO 3759,ASTM D751-2006
Standard Length	50m	DIN EN ISO 3759,ASTM D751-2006
Compatible Inks	Dye-sub Transfer	
Application	Banner, Light Curtain, Shower Curtain, Air Cloth	